




Código: 778606 Varilla HARRIS STAY-SYLV 15%-----c/f-



ALEACION	PLATA (Ag)%	FOSF. (P)%	ALCANCE DE FUNDIR		ESPACIO RECOMEN. ENTRE UNIONES mm (in.)
			°C sólidos	(°F) líquidos	
STAY-SILV 15	15	5.00	643 °C (1190°F)	804°C (1480°F)	.076/.152 (.003/.006)